

BLANK PAGE



Indian Standard

SPECIFICATION FOR FLEXIBLE INSULATING SLEEVING

PART 3 SPECIFICATIONS FOR INDIVIDUAL TYPES OF SLEEVINGS

Section 406 Glass Textile Sleeving with PVC Based Coating — High Breakdown Strength

भारतीय मानक

नम्य विद्युतरोधन स्लोविंगों को विशिष्टि

भाग 3 अलग-अलग स्लीविंग

अनुभाग 406 पी वी सी आधारित लेपनयुक्त उच्च भंजन सामध्यं वाली कांच वस्त्रादि की स्लीविंग

UDC 621:315:614:73-462

@ BIS 1990

BUREAU OF INDIAN STANDARDS MANAK BHAVAN, 9 BAHADUR SHAH ZAFAR MARG NEW DELHI 110002

FOREWORD

This Indian Standard (Part 3/Sec 406) was adopted by the Bureau of Indian Standards on 25 October 1989, after the draft finalized by the Solid Electrical Insulating Meterials Sectional Committee had been approved by the Electrotechnical Division Council.

This standard deals with flexible insulating sleevings. It consists of the following three parts;

- Part 1 Definitions and general requirements,
- Part 2 Methods of tests, and
- Part 3 Specifications for individual types of sleevings.

This standard covers the requirements for glass textile sleeving with PVC based coating high breakdown strength.

This standard should be read in conjunction with IS 11654 (Part 1): 1986 'Specification for flexible insulating sleeving: Part 1 Definitions and general requirements' and IS 11654 (Part 2): 1986 'Specification for flexible insulating sleeving: Part 2 Methods of test'.

In the preparation of this standard, assistance has been derived from IEC Doc: 15C (Central Office) 199, Sheet 406 glass textile sleeving with PVC based coating high breakdown strength, issued by the International Electrotechnical Commission (IEC).

For the purpose of deciding whether a particular requirement of this standard is complied with, the final value, observed or calculated, expressing the result of a test or analysis, shall be rounded off in accordance with IS 2:1960 'Rules for rounding off numerical values (revised)'. The number of significant places retained in the rounded off value should be the same as that of the specified value in this standard.

Indian Standard

SPECIFICATION FOR FLEXIBLE INSULATING SLEEVING

PART 3 SPECIFICATIONS FOR INDIVIDUAL TYPES OF SLEEVINGS

Section 406 Glass Textile Sleeving with PVC Based Coating - High Breakdown Strength

1 SCOPE

1.1 This standard (Part 3/Sec 406) covers the requirements for temperature index 105, glass sleeving using either braided or knitted construction coated with a continuous flexible coating based on polyvinyl chloride (PVC) or its co-polymers for blends thereof high breakdown strength.

2 REFERENCES

Indian Standards **2.1** The following are necessary adjuncts to this standard.

IS No.

Title

8504 (Part 1): 1977 Guide for determination of thermal endurance properites of electrical insulating materials: Part 1 Temperature indices and thermal endurance profiles

10810 (Part 53): 1984 Methods of test for cables: Part 53 Flammability test

11654 (Part 1):1986

Specification for flexible insulating sleeving: Part 1 Definitions and general requirements

11654 (Part 2): 1986

Specification for flexible insulating sleeving: Part 2 Methods of test

3 DESIGNATION

3.1 Sleeving covered in this standard shall be identified as given in 3.1 of Part 1 of this standard.

For example, IS 11654-3-406 Nominal bore size in mm-Colour code [Colour code shall be as given in 3.2 of IS 11654 (Part 1): 1986.]

4 COLOUR

4.1 Sleeving is normally available in the colours: black, white, red, yellow, blue, green, brown and green/yellow.

5 REQUIREMENTS

5.1 In addition to the general requirements given in IS 11654 (Part 1): 1986 requirements specified in this standard shall also be applicable.

5.2 Dimensions

The sleeving shall comply with the dimensional requirements given in Table 1.

5.3 Bending After Heating

When tested in accordance with 13 of IS 11654 (Part 2): 1986, there shall be no cracking or detachment of coating visible after bending around mandrels as shown in Table 2 after 96 hours at 130°C.

5.4 Bending at Low Temperature

When tested in accordance with 14 of IS 11654 (Part 2): 1986, there shall be no cracking or detachment of coating visible after bending around mandrel as shown in Table 2 while at -25°C.

5.5 Thermal Stability

When tested in accordance with Method 'A' in 11 of IS 11654 (Part 2): 1986 the indicator paper shall not show the change in colour in less than 20 minutes while at 200°C.

5.6 Resistance to Solering Heat

When tested in accordance with 7 of IS 11654 (Part 2): 1986, the sleeving shall not show sign of splitting.

NOTE — This test shall be applicable for sleeving having nominal bore dia up to and including 5 mm.

5.7 Thermal Endurance, TI

When tested in accordance with IS 8504 (Part 1): 1977, TI at 20 000 hours shall be minimum 105.

5.8 Flammability

When tested applying IS 10810 (Part 53): 1984, in accordance with 27 of IS 11654 (Part 2):1986.

Table 1 Dimensions

(Clause 5.2)

Nominal Bore mm	Tolerance on Bore mm		Wall Thickness mm	
	Bilateral (±)	Unilateral (±)	Min	Max
(1)	(2)	(3)	(4)	(5)
0·3 0·5 0·8 1·0 1·5 2·0 2·5 3·0 4·0	0.05 0·10 0·10 0·15 0·15 0·20 0·20 0·25	0·10 0·20 0·20 0·30 0·30 0·40 0·40 0·50	0°20 0°25 0°25 0°25 0°35 0°35 0°40 0°40 0°50	0·30 0·50 0·50 0·90 0·90 0·90 0·90
5.0	0.25	0.20	0 ·50	0-90
6.0 8.0 10.0 12.0 16.0	0°25 0°50 0°50 0°50 0°50	0·50 1·0 1·0 1·0 1·0	0·50 0·50 0· 65 0·65 0·65	0°90 1°20 1°20 1°20 1°20
20°0 25°0	0°50 0°50	1·0 1·0	0.65 0.65	1 ·20 1 ·2 0

NOTE - Only positive tolerance may be used, if agreed to between the purchaser and the supplier.

Flammability shall be minimum 60 seconds. In addition, the indicator flag on these tests shall not be burned away and cotton shall not get ignited by flaming or glowing drippings.

Table 2 Mandrel Diameter for Bending Tests

(Clauses 5.3 and 5.4)

Nominal Bore mm	Mandrel Diameter			
	After Heating	At Low Temperature		
(1)	(2)	(3)		
0`3	2	2		
0`5	3	3		
0`8	4	4		
1*0	5	5		
1*5	6	6		
2*0	8	8		
2*5	10	10		
3	12	12		
4	15	15		
5	18	18		
6	21	21		
8	2 7	27		
10	33	6		
12	40	6		
16	6	6		
20	6	6		
25	6	6		

5.9 Breakdown Voltage

5.9.1 Breakdown voltage shall be determined by any of shot bath test given in 21.2 and straight mandrel test, 25 mm electrode given in 21.2 of IS 11654 (Part 2): 1986.

5.9.2 The rate of voltage application shall be 500 V/second or such that the required breakdown value is reached between 10 and 20 seconds.

5.9.3 The requirements of breakdown voltage at room temperature, elevated temperature and damp heat when measured in accordance with 21.7 of IS 11654 (Part 2): 1986, shall be as given in Table 3.

5.10 Insulation Resistance

5.10.1 Insulation Resistance at Room Temperature

When tested in accordance with 22 of IS 11654 (Part 2): 1986, the insulation resistance shall be $10^3 \,\mathrm{M}\,\Omega$ (minimum).

5.10.2 Insulation Resistance after Temperature Heat

When tested in accordance with 22 of IS 11654 (Part 2): 1986, the insulation resistance shall be $10^2 \text{ M}\Omega$ (minimum).

Table 3 Requirements for Breakdown Voltage

(Clause 5.9.3)

		Shot Bath Test Using Straight Mandrel 25 mm Electrode		Straight Mandrel with 25 mm Electrode	
		Central Value (kV)	Lowest Individual Value (kV)	Central Value (kV)	Lowest Individual Value (kV)
Bre	eakdown voltage kV (Min)				
a)	At room temperature	5.0	4.0	7.0	5.0
b)	Elevated temperature (130°C)	2.8	2.2	2•0	1.2
′c)	After damp heat	2.5	2.0	2.8	1.0

5.11 Mould Growth

In case of agreement between the purchaser and the supplier, this requirement shall be tested for Scale 1 in accordance with IS 11654 (Part 2): 1986.

6 PACKAGING

6.1 Provisions of 9.1 of IS 11654 (Part 1): 1986,

shall apply.

7 MARKING

7.1 In addition to the details given in 10 of IS 11654 (Part 1): 1986 following information shall be labelled:

Construction of the Sleeving — braided or knitted.

Standard Mark

The use of the Standard Mark is governed by the provisions of the Bureau of Indian Standards Act, 1986 and the Rules and Regulations made thereunder. The Standard Mark on products covered by an Indian Standard conveys the assurance that they have been produced to comply with the requirements of that standard under a well defined system of inspection, testing and quality control which is devised and supervised by BIS and operated by the producer. Standard marked products are also continuously checked by BIS for conformity to that standard as a further safeguard. Details of conditions under which a licence for the use of the Standard Mark may be granted to manufacturers or producers may be obtained from the Bureau of Indian Standards.

Bureau of Indian Standards

BIS is a statutory institution established under the Bureau of Indian Standards Act, 1986 to promote harmonious development of the activities of standardization, marking and quality certification of goods and attending to connected matters in the country.

Copyright -

BIS has the copyright of all its publications. No part of these publications may be reproduced in any form without the prior permission in writing of BIS. This does not preclude the free use, in the course of implementing the standard, of necessary details, such as symbols and sizes, type or grade designations. Enquiries relating to copyright be addressed to the Director (Publications), BIS.

Revision of Indian Standards

Indian Standards are reviewed periodically and revised, when necessary and amendments, if any, are issued from time to time. Users of Indian Standards should ascertain that they are in possession of the latest amendments or edition. Comments on this Indian Standard may be sent to BIS giving the following reference:

Doc: No. ETD 2 (3026)

Amendments Issued Since Publication

Amend No.	Date of Issue	Text Affected
		· · · · · · · · · · · · · · · · · · ·

BUREAU OF INDIAN STANDARDS

Headquarters:

Manak Bhavan, 9 Bahadur Shah Zafar Marg, New Delhi 110002 Terephones: 331 01 31, 331 13 75

Telegrams: Manaksanstha (Common to all Offices)

Regional Offices:

-	
Central: Manak Bhavan, 9 Bahadur Shah Zafar Marg NEW DELHI 110002	$ \begin{cases} 331 & 01 & 31 \\ 331 & 13 & 75 \end{cases} $
Eastern: 1/14 C.I.T. Scheme VII M, V.I.P. Road, Maniktola CALCUTTA 700054	37 86 62
Northern: SCO 445-446, Sector 35-C, CHANDIGARH 160036	2 18 43
Southern: C.I.T. Campus, IV Cross Road, MADRAS 600113	41 29 16
Western: Manakalaya, E9 MIDC, Marol, Andheri (East) BOMBAY 400093	6 32 92 95

Branches: AHMADABAD. BANGALORE. BHOPAL. BHUBANESHWAR. COIMBATORE. FARIDABAD. GHAZIABAD. GUWAHATI. HYDERABAD. JAIPUR. KANPUR. PATNA. TRIVANDRUM.

AMENDMENT NO. 1 MARCH 1993 TO

IS 11654 (Part 3/Sec 406): 1989 SPECIFICATION FOR FLEXIBLE INSULATING SLEEVING

PART 3 SPECIFICATIONS FOR INDIVIDUAL TYPES OF SLEEVINGS

Section 406 Glass Textile Sleeving with PVC Based Coating — High Breakdown Strength

(Page 2, Table 1, Note) — Delete the Note.

(ETD 02)